

# **GH HILCOFLEX PU DRAG X-TREME**

# PREMIUM TPU DRAG HOSE FOR MANURE SPREADING

#### **MATERIAL CONSTRUCTION**

Heavy duty version, **special PU** grade for outstanding abrasion and puncture resistance.

These *puncture test results* show why HILCOFLEX PU DRAG X-TREME is the best option!

## Jacket lining:

- High-tenacity polyester yarn, circular woven
- Specially designed for high tensile strength, tight bending radii and very little elongation under pressure
- Totally embedded in the polyurethane, offering optimum protection against mechanical damage

# Lining and jacket:

- Thermoplastic polyether polyurethane, extruded through the weave in a special one-step production process
- Highly resistant to abrasion, 5–6 times longer service life than nitrile hoses
- Inside: Very smooth for minimal pressure loss
- Outside: Very smooth for good flexibility, thick-walled for unbeatable wear resistance

#### **ADVANTAGES**

- ✓ Outstanding resistance to abrasion
- Extremely tough, hard-wearing and durable
- Extremely high tensile strength
- ✓ Resistant to oil, gasoline and chemicals (see resistance table)
- ✓ Resistant to aging and ozone
- ✓ Lightweight and easy to use compared to material transport hoses made of rubber
- ✓ Stays flexible at cold temperatures

#### AT A GLANCE

### **Temperature ranges**

-50 °C bis 75 °C

(Specifications apply to Water)

#### Standard colors

green

#### Areas of application

- Transport hose between lagoon and field
- Drag hose to tow behind tractors
- Please note that some HILCOFLEX PU hose sizes can be used for both applications

#### CONTACT

# Gollmer & Hummel GmbH

Gässlesweg 23 75334 Straubenhardt

- T +49 (0) 7082 9434-0
- F +49 (0) 7082 9434-99
- E info@gollmer-hummel.com

#### **PRESSURES**

# **Working pressure:**

Specifications apply only to the hose (medium water,  $20\,^{\circ}$ C). The potential working pressure may be lower than specified above for hose lines with couplings due to the nominal pressure of the couplings or the type of assembly. For compressed air, the maximum working pressure is 25% of the burst pressure.

# Maximum working pressure:

Approval can only be given by the manufacturer upon clarification of the exact area of application.

# Order hose sample >>

#### DATASHEET METRIC

Inside diameter in mm	Weight in g/m	Wall thickness in mm	Working pressure in bar	Max. working pressure in bar	Burst pressure in bar	Tensile strength in kg
102	1700	4.6	14	17	42	14600
114	1900	4.6	14	17	42	16600
127	2100	4.7	14	17	42	18900
152	2800	4.9	11	13	32	26200

i Specifications apply only to the hose. The potential working pressure may be lower than specified above for hose lines with couplings due to the nominal pressure of the couplings or the type of assembly.