

# **GH PROGRESS UL**

# TYPE 3 FIRE HOSE WITH RUBBERIZED LINING & JACKET - UL LISTED

#### MATERIAL CONSTRUCTION

# Jacket lining:

- Warp: High-tenacity polyester
- Weft: Polyamide; circular woven
- The special jacket construction ensures outstanding adhesion and much lower pressure loss compared to a 100% polyester jacket lining
- Totally embedded in the rubber, offering optimum protection against mechanical damage

### Rubberized lining and jacket:

- Very high-grade NBR/PVC rubber compound, extruded through the weave in a special one-step production process
- Special additives in the compound guarantee outstanding resistance to aging and ozone

#### **ADVANTAGES**

- ✓ Very lightweight and highly flexible (also at extremely low temperatures)
- ✓ Small coil diameter
- Excellent resistance to aging and ozone
- ✓ Lining extremely resistant to seawater and a wide range of chemicals (see resistance table)
- Resistant to mildew and rot
- Easy to repair

#### AT A GLANCE

### **Temperature ranges**

-20 °C bis 80 °C

(Specifications apply to Water)

#### **Standard colors**

red

# Areas of application

- Refineries
- Chemical industry
- Military
- Airport fire departments
- Industrial and municipal fire departments
- Fire hose for tough conditions
- Refineries
- Chemical industry
- Military
- Airport fire departments
- Industrial and municipal fire departments
- Fire hose for tough conditions

### **CONTACT**

#### Gollmer & Hummel GmbH

Gässlesweg 23 75334 Straubenhardt

- T +49 (0) 7082 9434-0
- F +49 (0) 7082 9434-99
- E info@gollmer-hummel.com

#### **PRESSURES**

Specifications apply only to the hose (medium water, 20 °C). The potential working pressure may be lower than specified above for hose lines with couplings due to the nominal pressure of the couplings or the type of assembly.

BS 6391:2009 with British Instantaneous couplings: Ø 38–76 mm: max. working pressure 15 bar Ø 89: max. working pressure 12 bar

# Maximum working pressure:

Approval can only be given by the manufacturer upon clarification of the exact area of application.

# **Test pressure:**

Maintained for 1 min.: In accordance with BS 6391:2009: Ø 38-89: 22.5 bar

# Order hose sample >>

# DATASHEET METRIC

Inside diameter in mm	Weight in g/m	Wall thickness in mm	Working pressure in bar	Max. working pressure in bar	Burst pressure in bar	Approval
25	210	2.3	25	30	75	
38	300	2.3	16	20	50	BS 6391, Lloyds Registe
40	310	2.3	16	20	50	
42	320	2.3	16	20	50	
45	340	2.3	16	20	50	BS 6391, Lloyds Registe
52	400	2.5	16	20	50	DIN 14811, Lloyds Reg
55	420	2.5	16	20	50	
64	540	2.6	16	20	50	BS 6391, Lloyds Registe
70	600	2.8	16	20	50	BS 6391, Lloyds Registe
75	650	2.9	16	20	50	Lloyds Register
89	850	3	16	20	50	

i Specifications apply only to the hose. The potential working pressure may be lower than specified above for hose lines with couplings due to the nominal pressure of the couplings or the type of assembly.